Test Number: 291342

Independent J Textile

P.O. Box 1948

1503 Murray Ave.

Dalton, Georgia 30722-1948 • Phone 706-278-3013 • Fax 706-272-7057 • E-mail: info@ittslab.com

TEST REPORT

Customer: Karndean International, LLC

June 19, 2009

Subject: Specimens of the submitted sample were prepared and tested in accordance with

ASTM E 648-06 and/or Federal Test Method 372. NFPA 253

FLOORING RADIANT PANEL TEST

Sample Description

Karndean 3mm Tile & Plank

Test Assembly

Mounted on 6mm FRC Board (Using Premium Multi Purpose Adhesive)

Test Results	Specimen No. 1	Specimen No. 2	Specimen No. 3
Critical Radiant Flux Total Burn Length Flame Front Out	0.88 watts/cm ² 22.0 cm 10.0 minutes	0.90 watts/cm ² 21.0 cm 10.0 minutes	0.94 watts/cm² 19.0 cm 10.0 minutes

Average Critical Radiant Flux

0.91 watts/cm²

Estimated Standard Deviation

0.03 watts/cm²

3.4% coefficient of variation

Executive Vice President